

Supplementary data

Formation mechanism and particle size distribution optimization of large fly ash particles



Jiajun Du¹, Zixiu Jia^{2,3}, Zhongcan Yang^{2,3}, Yonggang Zhao¹, Chaoyang Zhu⁴, Yang Bai¹, Wen Tan⁴, Xilai Zhang^{2,3}, Jiamin Gao⁵ and Peipin Wang^{6,*}

¹ Technical Support Center, Guoyuan Power (Shendong Power) Co., Ltd., Xi'an, China

² Xi'an Thermal Power Research Institute Co., Ltd., Xi'an, China

³ Shaanxi Provincial Engineering Technology Research Center for Environmental Protection of Coal-fired Power Plant Boilers, Xi'an, China

⁴ State Grid Energy Hefeng Coal and Power Co., Ltd., Tacheng, China

⁵ Xi'an Yitong Thermal Engineering Technical Services Co., Ltd., Xi'an, China

⁶ School of Mechanical and Power Engineering, Zhengzhou University, Zhengzhou, China

* Correspondence author; E-mail: wppyyh@zzu.edu.cn.

Supplementary tables

Table S1. Coal quality analysis.

Item	Symbol	Unit	Coal 1	Coal 2	Coal 3	Coal 4	Coal 5	Coal 6
Total Moisture	Mt	%	6.90	3.40	2.90	16.90	4.30	15.90
Air-dried Moisture	Mad	%	2.48	1.19	1.08	9.83	1.41	7.74
Ash Content (As-received)	Aar	%	53.37	33.66	30.99	33.33	23.10	12.12
Volatile Matter (Dry Ash-free)	Vdaf	%	45.43	35.74	35.63	42.02	11.69	34.85
Carbon (As-received)	Car	%	27.65	50.77	53.31	37.13	66.10	59.99
Hydrogen (As-received)	Har	%	2.31	3.32	3.49	2.53	2.64	3.27
Nitrogen (As-received)	Nar	%	0.44	0.76	0.79	0.40	0.93	0.60
Oxygen (As-received)	Oar	%	8.42	5.91	5.21	8.80	0.98	7.55
Total Sulfur (As-received)	St,ar	%	0.91	2.18	3.31	0.91	1.95	0.57
Gross Calorific Value (As-received)	Qgr,v,ar	MJ/kg	10.65	20.20	21.35	14.13	25.02	23.03
Net Calorific Value (As-received)	Qnet,v,ar	MJ/kg	10.02	19.44	20.56	13.22	24.38	21.99
Net Calorific Value (As-received)	Qnet,v,ar	kcal/kg	2394	4644	4912	3158	5824	5253
Hardgrove Grindability Index	HGI	—	94	66	68	73	66	66
Deformation Temperature	DT	°C	> 1500	1500	1470	1250	1360	1150
Softening Temperature	ST	°C	> 1500	> 1500	> 1500	1270	1390	1230
Hemisphere Temperature	HT	°C	> 1500	> 1500	> 1500	1280	1400	1240
Flow Temperature	FT	°C	> 1500	> 1500	> 1500	1290	1410	1250
SiO ₂ in Coal Ash	SiO ₂	%	52.23	45.33	40.56	59.41	52.95	53.66
Al ₂ O ₃ in Coal Ash	Al ₂ O ₃	%	34.71	33.16	34.02	18.28	25.96	16.35
Fe ₂ O ₃ in Coal Ash	Fe ₂ O ₃	%	6.40	11.23	14.70	11.27	8.64	9.69
CaO in Coal Ash	CaO	%	1.48	4.38	4.33	3.19	6.17	10.86
MgO in Coal Ash	MgO	%	0.36	0.50	0.40	1.39	0.74	0.92
Na ₂ O in Coal Ash	Na ₂ O	%	0.80	0.74	0.59	0.64	0.33	0.83
K ₂ O in Coal Ash	K ₂ O	%	0.73	0.68	0.54	2.58	0.73	1.40
TiO ₂ in Coal Ash	TiO ₂	%	1.27	1.17	1.29	1.23	1.26	1.19
SO ₃ in Coal Ash	SO ₃	%	1.38	2.25	2.60	0.85	2.10	3.85
MnO ₂ in Coal Ash	MnO ₂	%	0.019	0.058	0.048	0.245	0.075	0.164
P ₂ O ₅ in Coal Ash	P ₂ O ₅	%	0.151	0.214	0.209	0.166	0.596	0.699



Copyright©2026 by the authors. Published by ELSP. This work is licensed under Creative Commons Attribution 4.0 International License, which permits unrestricted use, distribution, and reproduction in any medium provided the original work is properly cited.

Table S2. Particle size distribution of fly ash. Bold values indicate the proportion of fly ash particles smaller than 45 μm .

Item	Size Range	Unit	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Sample 5 (90% content)
Mass	> 200 mesh	g	0.1649	0.1433	0.3469	0.0279	0.044	0.1425	0.0928
	150–200 mesh	g	0.1473	0.2256	0.3749	0.0261	0.1066	0.1024	0.0629
	90–150 mesh	g	1.044	1.9769	2.3034	0.2001	1.597	0.8576	0.4067
	45–90 mesh	g	4.4199	5.0789	6.5983	1.8368	7.5959	3.512	3.7912
	< 45 mesh	g	19.2239	17.5753	15.3765	22.9091	15.6565	20.3855	20.6464
Coal Mass	—	g	18	18	18	15	5	15	—
Ash Mass	—	g	5	9	12	1	7	4	—
Proportion	> 200 mesh	%	0.66	0.57	1.39	0.11	0.18	0.57	—
	150–200 mesh	%	0.59	0.9	1.5	0.1	0.43	0.41	—
	90–150 mesh	%	4.18	7.91	9.21	0.8	6.39	3.43	—
	45–90 mesh	%	17.68	20.32	26.39	7.35	30.38	14.05	—
	< 45 μm	%	76.9	70.3	61.51	91.64	62.63	81.54	—

Table S3. Sulfur content and sulfur forms of the six coal samples.

No.	Item	Symbol	Unit	1	2	3	4	5	6
1	Total Sulfur (As-received)	St,ar	%	0.91	2.18	3.31	0.91	1.95	0.57
2	Total Sulfur (Air-dried)	St,ad	%	1	1.51	2.28	0.95	2.26	0.67
3	Sulfate Sulfur	Ss,ad	%	0.36	0.06	0.05	0.02	0.03	0.01
4	Pyritic Sulfur	Sp,ad	%	0.3	0.74	0.82	0.63	1.01	0.56
5	Organic Sulfur	So,ad	%	0.34	0.71	1.41	0.3	1.22	0.1

Table S4. Ignition temperatures and ignition grades of the six coal samples.

Coal Sample No.	Ignition Temperature IT	Ignition Grade
1	700	Difficult
2	720	Difficult
3	680	Middle
4	540	Extremely Easy
5	760	Difficult

Extremely Easy: $IT \leq 550^\circ\text{C}$; Easy: $550^\circ\text{C} < IT \leq 600^\circ\text{C}$; Middle: $600^\circ\text{C} < IT \leq 700^\circ\text{C}$; Difficult: $IT > 700^\circ\text{C}$.

Table S5. Results of the full-scale boiler combustion optimization tests.

Item	Unit	Base Case 1	Base Case 2	Base Case 3
Oxygen Concentration	%	3.1	3.6	4.1
Proportion of Fly Ash Particles > 45 μm	%	52.2	50.5	48.7
Primary Air Flow Rate	t/h	High Primary Air	Low Primary Air	-
Proportion of Fly Ash Particles > 45 μm	%	65.8	49.3	-
Overfire Air Damper Opening	%	25%	50%	80%
Proportion of Fly Ash Particles > 45 μm	%	62.2	49.3	47.8
Operating O_2	%	3.1	4.1	3.6
Total coal flow	t/h	148	144	140.4
Calorific value of coal	kcal/kg	3573	3722	3573
Sulfur content of coal	%	0.97	1.41	0.97
Separator speed	rpm	5	20	5
Burn-out damper opening	%	25	25	25
Primary air flow (A/B/C/D mills)	t/h	47/52/46/40	48/52/45/40	48/52/45/40
Proportion of Fly Ash Particles > 45 μm	%	52.2	65.8	50.5